

**CALCIUM PRODUCTS INC  
CALCIUM PRODUCTS INC  
2520 N LOOP DR STE 7100  
AMES IA 50010-8279**

**REPORT OF ANALYSIS**

For: (7294) CALCIUM PRODUCTS INC  
AG LIME ANALYSIS

Analysis	Level Found		Reporting		Method	Analyst- Date	Verified- Date
	As Received	Units	Limit				
Sample ID: <b>PLATTE AO9006</b>	Lab Number: <b>8677441</b>	Date Sampled: <b>2019-09-18</b>					
Moisture	5.1	%	0.1		SM 2540 G-(1997)	bjs0-2019/09/26	asl4-2019/09/27
Calcium (total)	18.9	%	0.01		MWL ME PROC 26	trh1-2019/09/26	asl4-2019/09/27
Magnesium (total)	11.1	%	0.01		MWL ME PROC 26	trh1-2019/09/26	asl4-2019/09/27
Total neutralizing value (CaCO <sub>3</sub> eq)	98.1	%	0.1		AOAC 955.01	eas2-2019/09/27	asl4-2019/09/27
ECCE	48.9	%	0.1		Calculation	Auto-2019/10/01	Auto-2019/10/01
% passing 4 sieve	99.4	%	0.1		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01
% passing 8 sieve	78.9	%	0.1		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01
% passing 20 sieve	49.6	%	0.1		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01
% passing 30 sieve	42.4	%	0.1		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01
% passing 60 sieve	27.1	%	0.1		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01
% passing 80 sieve	21.8	%	0.0		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01
% passing 100 sieve	19.9	%	0.1		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01
% passing 200 sieve	13.8	%	0.1		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01
% retained pan	13.8	%	0.1		ASTM E 276-13 (mod)	may8-2019/10/01	asl4-2019/10/01

The result(s) issued on this report only reflect the analysis of the sample(s) submitted.

Our reports and letters are for the exclusive and confidential use of our clients and may not be reproduced in whole or in part, nor may any reference be made to the work, the results, or the company in any advertising, news release, or other public announcements without obtaining our prior written authorization.

REPORT NUMBER

**19-274-4054**

REPORT DATE  
**Oct 01, 2019**

SEND TO  
**7294**

RECEIVED DATE  
**Sep 25, 2019**



13611 B Street • Omaha, Nebraska 68144-3693 • (402) 334-7770  
www.midwestlabs.com

**PAGE 2/3**

ISSUE DATE  
**Oct 01, 2019**

**CALCIUM PRODUCTS INC  
CALCIUM PRODUCTS INC  
2520 N LOOP DR STE 7100  
AMES IA 50010-8279**

**REPORT OF ANALYSIS**

For: (7294) CALCIUM PRODUCTS INC  
AG LIME ANALYSIS

Analysis	Level Found As Received	Units	Reporting Limit	Method	Analyst- Date	Verified- Date
----------	----------------------------	-------	--------------------	--------	------------------	-------------------

All results are reported on an AS RECEIVED basis.

For questions please contact:

Rob Ferris  
Account Manager  
rferris@midwestlabs.com (402)829-9871

The result(s) issued on this report only reflect the analysis of the sample(s) submitted.

Our reports and letters are for the exclusive and confidential use of our clients and may not be reproduced in whole or in part, nor may any reference be made to the work, the results, or the company in any advertising, news release, or other public announcements without obtaining our prior written authorization.

**CALCIUM PRODUCTS INC  
CALCIUM PRODUCTS INC  
2520 N LOOP DR STE 7100  
AMES IA 50010-8279**

**REPORT OF ANALYSIS**

For: (7294) CALCIUM PRODUCTS INC  
AG LIME ANALYSIS

**Detailed Method Description(s)****SM 2540 G**

Analysis follows MWL WC 060 which is based on SM 2540 G. A sample is weighed placed in a vacuum drying oven to drive off the moisture and re-weighed. The sample is then placed in a muffle furnace at 550°C, cooled, and re-weighed. The residue remaining is the ash and the mass lost is the volatile matter.

**ICP Analysis Fertilizers AOAC 985.01 (mod)**

Analysis follows MWL ME 026 which is based on AOAC 985.01. Samples have been prepared using MWL WC 056. Total minerals in fertilizers have been prepared by AOAC 957.02 using mineral acids and heat. Water soluble manganese is prepared by AOAC 972.03 and the other water soluble by AOAC 977.01. Sample analysis involves moving the sample extract into the ICP where it is nebulized and introduced into the high temperature plasma which energizes the electrons of the dissolved minerals/metals. As the energized electrons of the minerals/metals return to ground state, energy is released as light. The emitted wavelength(s) and light intensities are used to identify and quantitate the minerals/metals in the sample

**AOAC 955.01**

Analysis follows MWL WC 039 which is based on AOAC 955.01. A sample is treated with an excess of acid and then back-titrated with a known base to a phenolphthalein end point

**Calculation**

Analytical results are entered into applicable formulas to provide a calculated result which is reported.

**Wet Sieve**

Sample analysis follows MWL WC 070 which is based on ASTM E 276. A known mass of a solid is obtained and a pre-determined set of sieves obtained. The sample is placed on the upper most (largest screen size) and the sample washed with water to wash the materials through the sieves. The material retained on the individual sieves is removed and weighed and the percent of the total passing through the sieve is calculated and reported.

**Fertilizer Prep AOAC 957.02**

Samples are prepared using a combination of nitric acid and heat. The heating takes place in a block digester

The result(s) issued on this report only reflect the analysis of the sample(s) submitted.

**Our reports and letters are for the exclusive and confidential use of our clients and may not be reproduced in whole or in part, nor may any reference be made to the work, the results, or the company in any advertising, news release, or other public announcements without obtaining our prior written authorization.**