

**CALCIUM PRODUCTS INC  
CALCIUM PRODUCTS INC  
2520 N LOOP DR STE 7100  
AMES IA 50010-8279**

**REPORT OF ANALYSIS**

For: (7294) CALCIUM PRODUCTS INC  
Aglime  
St. Marys KS  
P43436

Analysis	Level Found		Reporting			Analyst- Date	Verified- Date
	As Received	Dry Weight	Units	Limit	Method		
Sample ID: Hamm Quarry	Lab Number: 70531951		Date Sampled: 2024-09-25				
Moisture	0.8		%	0.1	SM 2540 G-(2015)	jsp9-2024/10/02	eas2-2024/10/02
Calcium (total)	31.5	31.8	%	0.01	MWL ME PROC 26	Auto-2024/10/01	tat9-2024/10/07
Magnesium (total)	0.56	0.56	%	0.01	MWL ME PROC 26	Auto-2024/10/01	tat9-2024/10/07
Total neutralizing value (CaCO3 eq)	77.4		%	0.1	AOAC 955.01	jed2-2024/10/07	tat9-2024/10/07
ECCE	40.7		%	0.1	Calculation	Auto-2024/10/07	Auto-2024/10/07
% passing 4 sieve	98.4		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 8 sieve	74.8		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 10 sieve	70.0		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 20 sieve	49.0		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 30 sieve	42.9		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 40 sieve	38.5		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 50 sieve	35.2		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 60 sieve	33.8		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 80 sieve	31.5		%	0.0	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 100 sieve	30.4		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% passing 200 sieve	26.8		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02
% retained pan	26.8		%	0.1	ASTM E 276-13 (mod)	kae1-2024/10/02	eas2-2024/10/02

The result(s) issued on this report only reflect the analysis of the sample(s) submitted.

Our reports and letters are for the exclusive and confidential use of our clients and may not be reproduced in whole or in part, nor may any reference be made to the work, the results, or the company in any advertising, news release, or other public announcements without obtaining our prior written authorization.



13611 B Street • Omaha, Nebraska 68144-3693 • (402) 334-7770  
www.midwestlabs.com

CALCIUM PRODUCTS INC  
CALCIUM PRODUCTS INC  
2520 N LOOP DR STE 7100  
AMES IA 50010-8279

REPORT OF ANALYSIS  
For: (7294) CALCIUM PRODUCTS INC  
Aglime  
St. Marys KS  
P43436

Analysis	Level Found		Reporting		Analyst- Date	Verified- Date
	As Received	Dry Weight	Units	Limit		

For questions please contact:

*Vanessa Huxhold*

Vanessa Huxhold  
Account Manager  
vhuxhold@midwestlabs.com (402)807-1632

**CALCIUM PRODUCTS INC  
CALCIUM PRODUCTS INC  
2520 N LOOP DR STE 7100  
AMES IA 50010-8279**

**REPORT OF ANALYSIS**

For: (7294) CALCIUM PRODUCTS INC  
Aglime  
St. Marys KS  
P43436

**Detailed Method Description(s)****SM 2540 G**

Analysis follows MWL WC 060 which is based on SM 2540 G. A sample is weighed placed in a vacuum drying oven to drive off the moisture and re-weighed. The sample is then placed in a muffle furnace at 550°C, cooled, and re-weighed. The residue remaining is the ash and the mass lost is the volatile matter.

**ICP Analysis Fertilizers AOAC 985.01 (mod)**

Analysis follows MWL ME 026 which is based on AOAC 985.01. Samples have been prepared using MWL WC 056. Total minerals in fertilizers have been prepared by AOAC 957.02 using mineral acids and heat. Water soluble manganese is prepared by AOAC 972.03 and the other water soluble by AOAC 977.01. Sample analysis involves moving the sample extract into the ICP where it is nebulized and introduced into the high temperature plasma which energizes the electrons of the dissolved minerals/metals. As the energized electrons of the minerals/metals return to ground state, energy is released as light. The emitted wavelength(s) and light intensities are used to identify and quantitate the minerals/metals in the sample

**AOAC 955.01**

Analysis follows MWL WC 039 which is based on AOAC 955.01. A sample is treated with an excess of acid and then back-titrated with a known base to a phenolphthalein end point

**Calculation**

Analytical results are entered into applicable formulas to provide a calculated result which is reported.

**Wet Sieve**

Sample analysis follows MWL WC 070 which is based on ASTM E 276. A known mass of a solid is obtained and a pre-determined set of sieves obtained. The sample is placed on the upper most (largest screen size) and the sample washed with water to wash the materials through the sieves. The material retained on the individual sieves is removed and weighed and the percent of the total passing through the sieve is calculated and reported.

**Fertilizer Prep AOAC 957.02**

Samples are prepared by AOAC 957.02 using mineral acid and heat.

The result(s) issued on this report only reflect the analysis of the sample(s) submitted.

Our reports and letters are for the exclusive and confidential use of our clients and may not be reproduced in whole or in part, nor may any reference be made to the work, the results, or the company in any advertising, news release, or other public announcements without obtaining our prior written authorization.